



CARBON-AG

Granular Activated Carbon

Activity (ASTM 3467)	60 CTC
Particle Size	4x8 US MESH
Iodine number	950 mg/gm
Specific Surface Area (N2 Bet Method)	950 m ² /gm
Ash Content (ASTM 2866)	8% max
Abrasion Number	78 Minimum
Hardness (ASTM 3802)	95.0% Minimum
Moisture as Packed (ASTM 2867)	5% Maximum
Bulk Density	28 Lb/ft ³

